



## DOOR SLAB ONLY

TESTED IN ACCORDANCE WITH - CSA-A440 – NFRC THERMAL SOFTWARE					
THERMAL DATA – 6mm CARDINAL 366 LOW E #2//6mm CLEAR					
U-VALUE	W/M2-K	BTU/H-FT2F0	SHGC	CR	VT
	2.31	0.41	0.23	N/A	0.50
THERMAL DATA – 6mm CARDINAL 366 LOW E #2//6mm CARDINAL I89-6 LOW E #4					
U-VALUE	W/M2-K	BTU/H-FT2F0	SHGC	CR	VT
	2.07	0.36	0.23	N/A	0.49

## 250T DOOR WITH 2050 SERIES STOREFRONT

TESTED IN ACCORDANCE WITH - CSA-A440 – NFRC THERMAL SOFTWARE					
THERMAL DATA – 6mm SB60 LOW E #2//6mm CLEAR					
U-VALUE	W/M2-K	BTU/H-FT2F0	SHGC	CI	VT
	2.919	0.514	0.293	23.5	0.493

TESTING IN ACCORDANCE – ASTM E283					
AIR LEAKAGE	TEST PRESSURE	INFILTRATION	EXFILTRATION	OVERALL RESULT	NAFS 2017 REPRESENTATIVE TEST LEVEL
	75PA	0.985 L/S/M2 0.194 CFM/FT2	1.386 L/S/M2 0.273 CFM/FT2	<b>PASS</b>	<b>LEVEL A2</b>

TESTING IN ACCORDANCE – ASTM E331					
WATER PENETRATION					NAFS 2017 REPRESENTATIVE TEST LEVEL
					<b>PASS</b>

The above results relate only to the product configuration tested. Every effort has been taken to accurately report the performance of the material, however, due to large amount of input data and reliance from outside sources, it is possible that some errors and/or omissions may occur.