



DOOR SLAB ONLY

TESTED IN ACCORDANCE WITH - CSA-A440 – NFRC THERMAL SOFTWARE					
THERMAL DATA – 6mm CARDINAL 366 LOW E #2//6mm CLEAR					
U-VALUE	W/M2-K	BTU/H-FT2F0	SHGC	CR	VT
	2.27	0.40	0.22	N/A	0.46
THERMAL DATA – 6mm CARDINAL 366 LOW E #2//6mm CARDINAL I89-6 LOW E #4					
U-VALUE	W/M2-K	BTU/H-FT2F0	SHGC	CR	VT
	2.04	0.36	0.21	N/A	0.45

2000 SERIES GLACIER DOOR WITH 2435 SERIES CURTAIN WALL ADAPTER

TESTED IN ACCORDANCE WITH - CSA-A440 – NFRC THERMAL SOFTWARE					
THERMAL DATA – 6mm SB60 LOW E #2//6mm CLEAR					
U-VALUE	W/M2-K	BTU/H-FT2F0	SHGC	CI	VT
	2.954	0.52	0.274	30.8	0.461

TESTING IN ACCORDANCE – ASTM E283					
AIR LEAKAGE	TEST PRESSURE	INFILTRATION	EXFILTRATION	OVERALL RESULT	NAFS 2017 REPRESENTATIVE TEST LEVEL
	75PA	0.985 L/S/M2 0.194 CFM/FT2	1.386 L/S/M2 0.273 CFM/FT2	PASS	LEVEL A2

TESTING IN ACCORDANCE – ASTM E331					
WATER PENETRATION					NAFS 2017 REPRESENTATIVE TEST LEVEL
					PASS

The above results relate only to the product configuration tested. Every effort has been taken to accurately report the performance of the material, however, due to large amount of input data and reliance from outside sources, it is possible that some errors and/or omissions may occur.